

## 2mm/3mm Glue Down LVT: Data Sheet/Specifications

**Size:** 9"x48", 7.25"x48", 6"x36"

**Wear Layer:** 6-mil, 8-mil, 12-mil, 20-mil-(3mm Only)

**Texture:** Deep Embossed

**Thickness:** 2mm/3mm



Description	Results
<b>ASTMF1700</b> -(ASTMF2055, ASTM F386, ASTM F410, ASTM F2055, ASTM F1914, ASTM F137, ASTM F2199, ASTM F925, ASTM F2199, ASTM F1515, ASTM F1514, Certificate of Compliance)	Pass
<b>ANSIA.137 Dynamic Co-efficient of Friction</b>	Average DCOF .44
<b>ASTME648 Critical Radiant Flux of Floor Covering Systems</b>	Meets or exceeds Class 1 rating as specified in NFPA Life Safety Code 101 and IBC 804.2 Classification
<b>ASTME662 Smoke Density</b>	This sample passes the requirements of 450 or less
<b>ASTMF137 Flexibility of Resilient Flooring Materials</b>	Passes 6mm Mandrel
<b>ASTMF925-Resistant to Chemicals</b>	Pass
<b>ASTMF1514 Measuring Heat Stability-(7 Days)</b>	Test requirements of < 8.0 Delta E were met by the tested samples
<b>ASTMF1515-Measuring Light Stability of Flooring by color change</b>	Test requirements of < 8.0 Delta E were met by the tested samples
<b>ASTMF1914-(Short Term Indentation)</b>	Residual Indentation at 40 lbs-0.015 Inch (7.78%)
<b>ASTMF2199-(Dimensional Stability after exposure to heat)</b>	Length--0.008 Inch per 12 inches (-0.07%) Width-0.013 Inch per 12 inches (-0.11%)
<b>ASTMF2055-(Size, Tolerance)</b>	.016 in/lin ft
<b>ASTMF410-Thickness/Wear Layer</b>	Requirement: Commercial .02, Test Result: .011 inch/.26mm
<b>Certificate of Compliance</b>	Requirement: Max 1/3 of flat surface area/Test Result: Pass

## Glue Down LVT: (Featuring EIR Embossing)

### Sizes & Systems

Thickness	Sq Ft Per Carton	Boxes Per Pallet	Sq Ft Per Pallet	Sq Ft Per Container	Pallets Per Container
2mm	57	48	2700	54000	20
3mm	48	48	2304	46080	20



**Carmella Oak**



**Beech Oak**



**Vienna Grey**



**Vienna Maple**



**Carolina Maple**




**Pierre Oak**



**Iberian Maple**



**Magellan**



**Kenneth Maple**